

OLTEC rust preventive products

	Type of film	Flash point (°C)	VOC	Visco at 40°C (mm2/s)	Corrosion protection		Main applications
					Indoors	Outdoors unter shelter	
OLTEC Coat Bio 131	n/a	n/a	no	2	n/a	n/a	Biodegradable rust preventive for coolant systems and leakage internal tests
OLTEC Coat DW 63	n/a	> 63	yes	1	n/a	n/a	Dearomatized dewatering fluid. Quickly removes water from surfaces
OLTEC Coat 15	oily	> 34	yes	1	1 month	n/a	Inter-operation dewatering degreaser leaving an ultra-thin protective film
OLTEC Coat 1030 ES	oily	> 160	no	4	3 months	1 month	Highly dewatering ester base protection fluid. Without H304 labeling
OLTEC Coat 15L	oily	> 64	yes	3	6 months	1-2 months	Low odour rust preventive dewatering for metal parts after machining
OLTEC Coat 35	oily	> 34	yes	2,5	6 months	1 month	Dewatering rust preventive for metal parts and tools
OLTEC Coat 55	oily	> 34	yes	3	12-18 months	3 months	Dewatering long lasting rust preventive for metal parts and tools
OLTEC Coat 60	waxy	> 34	yes	5	18 months	4 months	Rust protection of metal parts, tools and plastic injection moulds
OLTEC Coat 98	waxy	> 34	yes	16	24 months	12 months	Very long-lasting rust preventive for maritime shipments
OLTEC Coat C 11024	waxy	> 110	no	24	6 months	3 months	Dewatering rust preventive without H304 labeling

n/a : non applicable